

Elastic Weft Yarn

ITEM	SPECIFICATIONS		
	22S	25S	28S
Linear Density (dtex)	270 ± 20	240 ± 20	210 ± 20
Breaking Strength (CN)	≥ 230	≥ 230	≥ 180
CV of Breaking Strength	≤ 7	≤ 7	≤ 7
Elongation @ Break (%)	≥ 180	≥ 180	≥ 220
CV of Elongation @ Break	≤ 9	≤ 9	≤ 9
Breaking Strength after Heating 240°C×4min (CN)	≥ 210	≥ 210	≥ 150
CV of Breaking Strength after Heating	≤ 7	≤ 7	≤ 7
Elongation @ Break after Heating 240°C×4min (%)	≥ 150	≥ 150	≥ 150
CV of Elongation @ Break after Heating	≤ 9	≤ 9	≤ 9